

**AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions, and listings, of claims in the application:

1. (Currently amended): A method of joining a pair of metal components comprising the steps of:
  - (a) placing a first metal component having a first exposed continuous surface and a second metal component having a second exposed surface in overlapping relationship to each other;
  - (b) providing a metal rivet having a head and a tip opposite the head for entering into the first and second components; and
  - (c) rotating the rivet about its longitudinal axis and simultaneously plunging the rivet through the first component continuous surface and into the second component, wherein the hardness of the metal rivet is substantially similar to the hardness of at least one of the first and second components, such that the metal of the rivet and the first and second components plastically deform; and
  - (d) solidifying the plasticized metal to produce a metallurgical bond joint between the rivet and each of the first and second components.
2. (Currently amended): The method of claim 1, wherein the rivet tip is pointed.
3. (Currently amended): The method of claim 2, wherein a final position of the rivet tip is within the second component.

4. (Currently amended): The method of claim 3, wherein the rivet tip raises a portion of the second exposed surface.

5. (Currently amended): The method of claim 4, wherein the raised portion has a semispherical configuration.

6. (Currently amended): The method of claim 4, wherein the first and second components are held together between a clamp positioned on the first exposed surface and a backing anvil positioned against the second exposed surface, wherein the backing anvil defines a recess which receives the raised portion and deforms the raised portion into the configuration of the recess.

7. (Currently amended): The method of claim 2, wherein a final position of the rivet tip is flush with the second exposed surface.

8. (Currently amended): The method of claim 7, wherein the first and second components are held together between a clamp positioned on the first exposed surface and a backing anvil positioned against the second component, wherein the backing anvil has a substantially planar surface against which the rivet abuts to maintain the rivet tip flush with the second exposed surface.

9. (Currently amended): The method of claim 2, wherein a final position of the rivet tip exterior to the second component.

10. (Currently amended): The method of claim 1, wherein at least one of the first and second components is preheated prior to plunging the rivet therein.

11. (Currently amended): The method of claim 1, wherein the rivet defines a helical groove along an exterior surface of the rivet.

12. (Currently amended): The method of claim 1, wherein the rivet includes means for hiding flash produced in the step of plunging and rotating the rivet.

13. (Currently amended): The method of claim 12, wherein the rivet includes a flange and a lip extending therefrom, the flange and lip thereby defining a recess for collecting flash between the rivet and the first exposed surface.

14. (Currently amended): The method of claim 1, wherein the rivet tip defines a bore.

15. (Currently amended): The method of claim 14, wherein the bore extends partially through the rivet.

16. (Currently amended): The method of claim 14, wherein the bore extends completely through the rivet.

17. (Currently amended): The method of claim 1, wherein the head of the rivet includes means for engaging another component.

18. (Currently amended): The method of claim 1, further comprising joining a third metal component to the second component by the steps of:

(i) positioning the third component having a third exposed surface in overlapping relationship to the second exposed surface;

(ii) providing another metal rivet having a head and a tip opposite the head for entering into the third and second components; and

(iii) rotating the other rivet about its longitudinal axis and simultaneously plunging the other rivet through the third component exposed surface and into the second component, wherein the hardness of the other metal rivet is substantially similar to the hardness of one of the third and second components.

19. (Currently amended): The method of claim 18, wherein the third exposed surface defines a pilot hole into which the other rivet is positioned prior to step (iii).

20. (Currently amended): The method of claim 18, wherein steps (c) and (iii) are performed simultaneously.

21. (Currently amended): The method of claim 1, further comprising removing the rivet head following step (d).

22. (Currently amended): The method of claim 21, wherein the rivet head is joined to a main portion of the rivet via a narrowed portion such that when the plasticized metal solidifies, the rivet head breaks off at the narrowed portion from the rivet main portion.

23. (Currently amended): The method of claim 1, wherein the first and second metal components and the rivet each comprise aluminum or an aluminum alloy.

24. (Currently amended): The method of claim 23, wherein at least one of the first and second metal components is a clad product.

25. (Previously Amended): A composite metal product produced according to the method of claim 1.

26. (Currently amended): The composite metal product of claim 25, wherein the first metal and second metal components and the rivet each comprise aluminum or an aluminum alloy.

27. (Currently amended): The composite metal product of claim 26, wherein at least one of the first and second metal components is a clad product.

28. (Currently amended): The composite metal product of claim 25, wherein at least about 50% of the alloying components the first and second components and the rivet are the same.

29. (Currently Amended): A system for joining a first metal component to a second metal component with a rivet, wherein the hardness of the rivet is substantially similar to the hardness of at least one of the first and second components, said system comprising:

a clamp positioned on a continuous first exposed surface of the first component for maintaining the first component adjacent the second component;

a backing anvil for supporting a second exposed surface of the second component adjacent the first component; and

means for rotating and plunging the rivet through the continuous first exposed surface and into the second component to produce a region of plasticized metal between the rivet and each of the first and second components, the plasticized metal being solidifiable to form a ~~friction-weld~~ metallurgical bond between the rivet and each of the first and second components.

30. (Currently amended): The system of claim 29, further comprising means for removing flash produced when the rivet is friction welded to the first and second components.

Application No. 10/025,402  
Amendment Dated November 5, 2003  
In Reply to USPTO Office Action dated September 3, 2003  
Confirmation No. 4915  
Attorney Docket No. 4430-011286  
Alcoa Docket No. 00-2521

31. (Currently amended): The system of claim 29, [where ] wherein said means for removing flash comprises a moveable member linked to said means for rotating, said moveable member configured to move about the rivet to remove the flash.

32. (Currently amended): The system of claim 31, wherein said rotating means is disengagable from the rivet to allow the friction weld to solidify while said moveable member continues to move about the rivet.